

## TEST REPORT

Applicant: RAM QUALITY PRODUCTS LTD  
15 MENDES ST  
RAMAT-GAN 52653  
ISRAEL

Number: HKGH02578338 S1

Date: Apr 22, 2020

Attn: EREZ BEN MOSHE

*This is to supersede Report No. HKGH02578338 dated Apr 22, 2020 due to information update*

Submitted sample said to be :  
Item Name : **Foldable Playhouse**  
Style No. : **710101**  
Quantity : 1 set  
Labelled Age Group : Not Specified  
Packaging Provided : No  
Country of Origin : Israel

\*\*\*\*\*

For and on behalf of :  
Intertek Testing Services HK Ltd.



Cindy I.K. Chan  
Vice President



# TEST REPORT

Number : HKGH02578338 S1

**Conclusion:**

The submitted sample was tested under the following requirements requested by the applicant, subject to the information stated in the remark and attached page(s) for details :

<u>Requirement</u>	<u>Result</u>
(1) AS/NZS ISO 8124-3:2003 (Australian Trade Practice Act 1974 with Consumer Protection Notice no. 1, 2009 - Consumer Product Safety Standard for Lead and certain elements in children's toys.) - Toxic elements test	Pass
AS/NZS 8124-3:2012/Amdt 1:2016 - Toxic elements test	Pass
(2) Australian Competition and Consumer Act 2010 with Consumer Protection Notice No. 11, 2011 - Permanent ban on children's products with Diethylhexyl Phthalate (DEHP)	Pass
(3) ASTM F963-17 - Soluble heavy elements test	Pass
(4) ASTM F963-17 - Total Lead content	Pass
(5) U.S. CFR Title 16 (CPSC Regulations) - Part 1303 - Total Lead content in surface coating	Not Applicable
U.S. Consumer Product Safety Improvement Act 2008 Title I Section 101 - Total Lead content in surface coating	Not Applicable
(6) U.S. Consumer Product Safety Improvement Act 2008 Title I Section 101 - Total Lead content in non-surface coating materials (substrate)	Pass
(7) US CPSC 16 CFR Part 1307 Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates effective from April 25, 2018 - Phthalate content	Pass

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

<u>Requirement</u>	<u>Result</u>
(8) California Proposition 65 for toys, Consent Judgement no. RG-356892 - Lead content	Pass
(9) Illinois Lead Poisoning Prevention Act 410 ILCS 45 - Total Lead content	Pass
(10) California Proposition 65 for Toys (designed for or reasonable used by children under six years of age), Consent judgment no. BG-350969 - Phthalate content	Pass
(11) EN 71-3:2019 - Migration of certain elements	Pass
(12) REACH Regulation (EC) No.1907/2006 , Annex XVII Item 23 & amendment No. 2016/217 - Cadmium content requirement	Pass
(13) REACH Regulation (EC) no. 1907/2006, Annex XVII Items 51 & 52, amendment no. 552/2009 & 2018/2005 (Placed on the market after 7 July 2020) - Phthalates content	Pass
(14) REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 Annex XVII Item 50 - Polycyclic aromatic hydrocarbons content	Pass
(15) REACH Regulation (EC) No. 1907/2006, Annex XVII item 20 & amendment (EU) No. 276/2010 - Organotin content requirement	Pass
(16) Regulation (EC) No. 2019/1021 on persistent organic pollutants (POPs) - Short Chain Chlorinated Paraffin (C10 - C13) (SCCP) content	Pass
(17) EU Commission Directive 2017/774 amending Appendix C of Annex II to Directive 2009/48/EC on the safety of toys - Phenol migration content	Pass

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(1) Toxic Elements Analysis

Test Method : Acid extraction method was used and toxic elements content were determined by Inductively Coupled Argon Plasma Spectrometry.

Materials other than modelling clay:

	Result (mg/kg)			Limit (mg/kg)
	(1)	(2)	(3)	
Soluble Barium (Ba)	<5	<5	<5	1000
Soluble Lead (Pb)	<5	<5	<5	90
Soluble Cadmium (Cd)	<5	<5	<5	75
Soluble Antimony (Sb)	<5	<5	<5	60
Soluble Selenium (Se)	<5	<5	<5	500
Soluble Chromium (Cr)	<5	<5	<5	60
Soluble Mercury (Hg)	<5	<5	<5	60
Soluble Arsenic (As)	<2.5	<2.5	<2.5	25

	Result (mg/kg)		Limit (mg/kg)
	(4)	(5)	
Soluble Barium (Ba)	<5	<5	1000
Soluble Lead (Pb)	<5	<5	90
Soluble Cadmium (Cd)	<5	<5	75
Soluble Antimony (Sb)	<5	<5	60
Soluble Selenium (Se)	<5	<5	500
Soluble Chromium (Cr)	<5	<5	60
Soluble Mercury (Hg)	<5	<5	60
Soluble Arsenic (As)	<2.5	<2.5	25

mg/kg = milligram per kilogram

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(2) Diethylhexyl Phthalate (DEHP) Content

Test Method : Australian Competition and Consumer Act 2010 with Consumer Protection Notice No. 11, 2011, by solvent extraction and followed by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Tested Component	Result in %, w/w	Limit in %, w/w
(1/2/3)	<0.01	1
(4/5)	<0.01	1

The above limit was quoted according to Australian Competition and Consumer Act 2010 with Consumer Protection Notice No. 11, 2011 on Diethylhexyl Phthalate (DEHP) for children's products

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

### (3) Heavy Elements Analysis

Test Method : Sections 8.3.2, 8.3.3, 8.3.4 and 8.3.5 of the ASTM Standard Consumer Safety Specification for Toy Safety F963-17, acid extraction and analysed by Inductively Coupled Argon Plasma Spectrometry.

Materials other than modelling clay:

	Result (ppm)			Limit (ppm)
	(1)	(2)	(3)	
Soluble Barium (Ba)	<5	<5	<5	1000
Soluble Lead (Pb)	<5	<5	<5	90
Soluble Cadmium (Cd)	<5	<5	<5	75
Soluble Antimony (Sb)	<5	<5	<5	60
Soluble Selenium (Se)	<5	<5	<5	500
Soluble Chromium (Cr)	<5	<5	<5	60
Soluble Mercury (Hg)	<5	<5	<5	60
Soluble Arsenic (As)	<2.5	<2.5	<2.5	25

	Result (ppm)		Limit (ppm)
	(4)	(5)	
Soluble Barium (Ba)	<5	<5	1000
Soluble Lead (Pb)	<5	<5	90
Soluble Cadmium (Cd)	<5	<5	75
Soluble Antimony (Sb)	<5	<5	60
Soluble Selenium (Se)	<5	<5	500
Soluble Chromium (Cr)	<5	<5	60
Soluble Mercury (Hg)	<5	<5	60
Soluble Arsenic (As)	<2.5	<2.5	25

ppm = parts per million = mg/kg

#### Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(4) Total Lead (Pb) Content

Test Method : Sections 4.3.5.1(1) and 4.3.5.2(2)(a) of the ASTM Standard Consumer Safety Specification for Toy Safety F963-17, CPSC-CH-E1001-08.3, CPSC-CH-E1002-08.3 or/and CPSC-CH-E1003-09.1, analysed by Inductively Coupled Argon Plasma Spectrometry.

Substrate:

Tested Component	Result in ppm	Limit in ppm
(1/2/3)	<20	100
(4/5)	<20	100

ppm = parts per million = mg/kg

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020  
Test Period : Apr 09, 2020 to Apr 16, 2020

(5) Total Lead (Pb) Content in Surface Coating

Test Method : Standard Operating Procedure for Determining Lead (Pb) in Paint and Other Similar Surface Coatings, test method CPSC-CH-E1003-09.1, analysed by Inductively Coupled Argon Plasma Spectrometry.

Date sample received : Apr 09, 2020  
Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(6) Total Lead (Pb) Content in Non-Surface Coating Materials (Substrate)

Test Method : Standard Operating Procedures for Determining Total Lead (Pb) in Children's Products, test methods CPSC-CH-E1002-08.3 and/or CPSC-CH-E1001.08.3, analysed by Inductively Coupled Argon Plasma Spectrometry.

Tested Component	Result in ppm	Limit in ppm
(1/2/3)	<20	100
(4/5)	<20	100

ppm = parts per million = mg/kg

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020  
Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(7) Phthalate Content Test

Test Method : Standard Operating Procedure for Determining Phthalates, test method CPSC-CH-C1001-09.4 was used and phthalate content was determined by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Compound	Result (%, w/w)		Limit (%, w/w)
	(1/2/3)	(4/5)	
Dibutyl phthalate (DBP)	<0.01	<0.01	0.1
Diethyl hexyl phthalate (DEHP)	<0.01	<0.01	0.1
Benzyl butyl phthalate (BBP)	<0.01	<0.01	0.1
Diisononyl phthalate (DINP)	<0.01	<0.01	0.1
Diisobutyl phthalate (DIBP)	<0.01	<0.01	0.1
Di-n-pentyl phthalate (DPP) / (DPENP)	<0.01	<0.01	0.1
Di-n-hexyl phthalate (DNHP) / (DHEXP)	<0.01	<0.01	0.1
Dicyclohexyl phthalate (DCHP)	<0.01	<0.01	0.1

The above limits are quoted from Federal Register, Vol. 82, No. 207, October 27, 2017, Rules and Regulations, Final rule for 16 CFR Part 1307 "Prohibition of Children's Toys and Child Care Articles Containing Specified Phthalates" effective from April 25, 2018.

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020  
Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(8) Total Lead (Pb) content

Test Method : Acid digestion and analysed by Inductively Coupled Argon Plasma Spectrometry.

Substrate:

Tested Component	Result in %, w/w	Limit in %, w/w
(1/2/3)	<0.0020	0.010
(4/5)	<0.0020	0.010

The above limit was quoted from the Consent Judgement no. RG-356892 settled by Superior Court of the State of California for the County of Alameda, for toys based on the California Proposition 65.

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(9) Total Lead (Pb) content

Test Method : Illinois Lead Poisoning Prevention Act 410 ILCS 45, acid digestion method and analysed by Inductively Coupled Argon Plasma Spectrometry.

Substrate:

Tested Component	Result in %, w/w	Limit in %, w/w
(1/2/3)	<0.0020	0.010
(4/5)	<0.0020	0.010

Warning statement limit for coating = 0.0040%

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(10) Phthalate Content Test

Test Method : Solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Compound	Result (% w/w)		Limit (% w/w)
	(1/2/3)	(4/5)	
Dibutyl phthalate (DBP)	<0.01	<0.01	0.1
Diethyl hexyl phthalate (DEHP)	<0.01	<0.01	0.1
Benzyl butyl phthalate (BBP)	<0.01	<0.01	0.1
Diisodecyl phthalate (DIDP)	<0.01	<0.01	0.1
Di-n-hexyl phthalate (DNHP)	<0.01	<0.01	0.1
Diisononyl phthalate (DINP)	<0.01	<0.01	--

The above limit was quoted from the Consent Judgment no. BG-350969 settled by superior court of the state of California for the county of Alameda, for Toys (designed for or reasonable used by children under six years of age) set based on the California Proposition 65.

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(11) 19 Toxic Element Migration Test

Test Method : EN 71-3:2019. Acid extraction method was used and toxic elements content were determined by Inductively Coupled Argon Plasma Spectrometry and Ion Chromatography- Inductively Coupled Plasma-Mass Spectrometry and/or Gas Chromatographic - Mass Spectrometry

Category (III): Scraped-off toy material:

	Result (mg/kg)			Limit (mg/kg)
	(1)	(2)	(3)	
Soluble Aluminium (Al)	<300	<300	<300	70000
Soluble Antimony (Sb)	<10	<10	<10	560
Soluble Arsenic (As)	<10	<10	<10	47
Soluble Barium (Ba)	<10	<10	<10	18750
Soluble Boron (B)	<50	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	<10	130
Soluble Copper (Cu)	<10	<10	<10	7700
Soluble Lead (Pb)	<10	<10	<10	23
Soluble Manganese (Mn)	<10	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	<10	94
Soluble Nickel (Ni)	<10	<10	<10	930
Soluble Selenium (Se)	<10	<10	<10	460
Soluble Strontium (Sr)	<100	<100	<100	56000
Soluble Tin (Sn)	<10	<10	<10	180000
Soluble Organic tin ++	<2.0	<2.0	<2.0	12
Soluble Zinc (Zn)	<100	<100	<100	46000

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

	Result (mg/kg)		Limit (mg/kg)
	(4)	(5)	
Soluble Aluminium (Al)	<300	<300	70000
Soluble Antimony (Sb)	<10	<10	560
Soluble Arsenic (As)	<10	<10	47
Soluble Barium (Ba)	<10	<10	18750
Soluble Boron (B)	<50	<50	15000
Soluble Cadmium (Cd)	<5	<5	17
Soluble Chromium (III) (Cr III)	<10	<10	460
Soluble Chromium (VI) (Cr VI)	<0.025	<0.025	0.053
Soluble Cobalt (Co)	<10	<10	130
Soluble Copper (Cu)	<10	<10	7700
Soluble Lead (Pb)	<10	<10	23
Soluble Manganese (Mn)	<10	<10	15000
Soluble Mercury (Hg)	<10	<10	94
Soluble Nickel (Ni)	<10	<10	930
Soluble Selenium (Se)	<10	<10	460
Soluble Strontium (Sr)	<100	<100	56000
Soluble Tin (Sn)	<10	<10	180000
Soluble Organic tin ++	<2.0	<2.0	12
Soluble Zinc (Zn)	<100	<100	46000

mg/kg = milligram per kilogram

++ : Unless the test result was marked with "Δ", Organic tin content was not directly determined and was derived from migration result of total tin.

Organic tin test result was expressed as tributyl tin.

Chromium (III) value was calculated as difference between migration results of total Chromium and Chromium (VI).

The new aluminium migration limit [2250mg/kg for Category (I), 560mg/kg for category (II) and 28130mg/kg for Category (III)] was quoted from directive (EU) 2019/1922 amending 2009/48/EC effective from 20 May 2021.

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020  
Test Period : Apr 09, 2020 to Apr 16, 2020

(12) Cadmium (Cd) Content

Test Method : Acid digestion method was used and total Cadmium content was determined by Inductively Coupled Argon Plasma Spectrometry.

Tested Component	Result in %, w/w	Limit in %, w/w
(1/2/3)	ND	0.01
(4/5)	ND	0.01

ND : Not detected (< 0.0005%)

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020  
Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



**TEST REPORT**

Number : HKGH02578338 S1

(13) Phthalate Content Test

Test Method : ISO 8124-6 : 2018 method A with internal standard calibration, by Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Seven Phthalates content:

Compound	Result (% w/w)		Limit (% w/w)
	(1/2/3)	(4/5)	
Dibutyl phthalate (DBP)	<0.01	<0.01	--
Diethyl hexyl phthalate (DEHP)	<0.01	<0.01	--
Benzyl butyl phthalate (BBP)	<0.01	<0.01	--
Diisobutyl phthalate (DIBP)	<0.01	<0.01	--
Sum of DBP, DEHP, BBP & DIBP	<0.01	<0.01	0.1
Diisononyl phthalate (DINP)	<0.01	<0.01	--
Di-n-octyl phthalate (DnOP)	<0.01	<0.01	--
Diisodecyl phthalate (DIDP)	<0.01	<0.01	--
Sum of DINP, DnOP & DIDP	<0.01	<0.01	0.1

The above limit was quoted according to Annex XVII Items 51 & 52 of the REACH Regulation (EC) no. 1907/2006, amendment no. 552/2009 taking into account the (EU) regulation 2018/2005 modifying entry 51 for which the DIBP shall not be placed on the market after 7 July 2020 in toys or childcare articles, individually or in any combination with the first three phthalates which already exist in the entry 51, in a concentration equal to or greater than 0,1 % by weight of the plasticised material.

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 16, 2020

\*\*\*\*\*



Page 16 of 21



# TEST REPORT

Number : HKGH02578338 S1

(14) Polycyclic Aromatic Hydrocarbons (PAH) Content

Test Method : Solvent extraction and determined by Gas Chromatographic - Mass Spectrometry (GC/MS).

Compound	Result (ppm)		Limit (ppm)
	(1/2/3)	(4/5)	
Benzo(a)pyrene	<0.10	<0.10	0.5
Benzo(e)pyrene	<0.10	<0.10	0.5
Benzo(a)anthracene	<0.10	<0.10	0.5
Chrysene	<0.10	<0.10	0.5
Benzo(b)fluoranthene	<0.10	<0.10	0.5
Benzo(j)fluoranthene	<0.10	<0.10	0.5
Benzo(k)fluoranthene	<0.10	<0.10	0.5
Dibenzo(a,h)anthracene	<0.10	<0.10	0.5

The above limit was quoted according to Annex XVII Items 50 of the REACH Regulation (EC) no. 1907/2006 & amendment (EU) no. 1272/2013 for polycyclic aromatic hydrocarbons (PAH).

ppm = parts per million = mg/kg

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020  
Test Period : Apr 09, 2020 to Apr 17, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(15) Organotin Content

Test Method : By solvent extraction, followed by Gas Chromatography Mass Spectrometric (GC/MS) analysis.

Compound	Result (% w/w)		Limit (% w/w)
	(1/2/3)	(4/5)	
Tri-substituted Organotin <sup>^</sup>	<0.005	<0.005	0.1
Dibutyltin (DBT)	<0.005	<0.005	0.1
Diocetyl tin (DOT)	<0.005	<0.005	0.1

The above limit was quoted according to Annex XVII Item 20 of the REACH Regulation (EC) no. 1907/2006 & amendment (EU) No. 276/2010 (formerly known as Decision 2009/425/EC) for organotin content.

<sup>^</sup> = The reported value was calculated by summation of the values of Tri-butyltin, Tri-phenyltin, Tri-methyltin, Tri-octyltin, Tri-cyclohexyltin

Detection limit = 0.005% (w/w) of tin

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 20, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(16) Short Chain Chlorinated Paraffin (C10 - C13) (SCCP) Content

Test Method : Solvent extraction and followed by Gas Chromatographic - Negative Chemical Ionization - Mass Spectrometry (GC-NCI-MS) Analysis.

Tested Component	Result in %, w/w
(1/2/3)	<0.01
(4/5)	<0.01

Requirement: 0.15% (w/w)

Detection limit = 0.01% (w/w)

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 20, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1

(17) Phenol Migration Content

Test Standard : EN71 Part 10 and 11 : 2005.

Tested Component	Result in mg/l	Limit in mg/l
(1)	<1	5
(2)	<1	5
(3)	<1	5
(4)	<1	5
(5)	<1	5

The above limit was quoted according to EU Commission Directive 2017/774 amending Appendix C of Annex II to Directive 2009/48/EC of the European Parliament and of the Council on the safety of toys, as regards Phenol with effective date on 4 November 2018.

mg/l = milligram per litre

Tested Components:

- (1) Turquoise plastic (roof).
- (2) Blue plastic (door).
- (3) Red plastic (roof).
- (4) Yellow plastic (tools).
- (5) Cream plastic (front window top, front door top, side, front window, door).

Date sample received : Apr 09, 2020

Test Period : Apr 09, 2020 to Apr 20, 2020

\*\*\*\*\*



# TEST REPORT

Number : HKGH02578338 S1



\*\*\*\*\*

End of report

*Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.*

*This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.*

*This report shall not be reproduced, except in full.*



